

BP125

Clear PU sealer- High solid

Technical data sheet Revision: 01/06/2024

PRODUCT OVERVIEW

General properties	Clear PU sealer with good thixotropy and sandability. High solid
Recommended use	Doors, chairs, kitchen doors
Application method	Spray gun, airless, airmix
Mix preparation	50% by volume. To be reduced with standard PU thinner S50 or S41 up to 20% by volume.
Colour available	Clear
Gloss available	-

CHEMICAL AND PHYSICAL CHARACTERISTICS (20 °C)

Solid Content (%)	45.0% ±0.2
Density (g/cm ³)	0.98 ±0.05
Viscosity DIN 4 (sec)	120"
Pot life	2 hours with standard hardener

APPLICATION PROPERTIES

Vertical hold (microns)	140
Recommended N° of coats	From 1 to 2
Recommended quantity per coat (g/m ²)	120-150
Metric yield (m ² /kg)	6-8

APPLICATION INSTRUCTIONS

Equipment	Dilution %	Nozzle	Press. air / bar	Press. varnish / bar
Air Mix	-	09-11	1-2	80-110
Air Less	-	09-11	--	120-150

DRYING

 Dry at 20°C and UR% between 45 - 65: 120 g/m²

Dust free	20 min
Handling	40 min
Overcoat	4 hours
Stackable	12 hours
Sanding	6 hours

 Dry in tunnel: 120 g/m²

Stage	Temperature	Time
Flash Off	20-25	15 min
Laminar Air	35-40	30 min
Cooling	20-25	15 min

RECOMMENDED CYCLE

1. Sand the wooden substrate with proper sanding papers
2. Apply from 1 to 2 coats of BP125
3. After proper drying time, sand the sealer with sanding paper 240-320
4. Overcoat with clear PU top coat TP151-XX

DISCLAIMER

The data provided in this technical sheet correspond to the values and characteristics of the product offered, in relation to our skills and experience. GALA-PRO guarantees the physical-chemical characteristics of its products, as well as their consistency. However, responsibility for the final result of the product application rests with the user, who must ensure that the selected product corresponds to their application needs and to the type of substrate selected. The viscosity level of highly thixotropic products may differ from the value reported in this technical data sheet; to be considered acceptable, this value should differ by a maximum of 30% from the reported value.